



ARFINO

PRECISION TURNING TECHNOLOGY

CC470K LEAD-FREE BRONZE RG+

DESIGNATION

DIN EN symbol CuSn4Zn2PS

DIN EN CC470K

COMPOSITION

Cu 90.0-96.0 %

Pb < 0.10 %

Sn 3.0-5.0 %

Ni < 0.3 %

S 0.2-0.6 %

(Reference values in % by weight)

APPLICATION

Meets all REACH and RoHS requirements and the limit value for lead in the Drinking Water Directive.

No cold brittleness (can be used up to -176 °C)

CORROSION RESISTANCE

High corrosion resistance and longevity and no risk of stress corrosion cracking

NOTE: This data sheet is for general information only.

Offices & Production

Via C. Musati, 3 - Z.I. Roccapietra
13019 Varallo S. (VC) – ITALY
P.iva: 00273120022

Warehouse & Shipping

Via Al Sesia, 2 - Z.I. Roccapietra
13019 Varallo S. (VC) – ITALY

PHONE: +39 0163.52465

FAX: +39 0163.54015

MAIL: info@officinearfino.it

WWW.OFFICINEARFINO.IT